

Ortho White Stone Plaster



Description: For crown and bridge, dies and cast partials. For basing dental arches and opposing models. For making study models. In use where economical yet tough, non-brittle and durable models are required

Packing	Product Code
(White) 30kg polyester gunny / paper bag.	4102/030

Type: IV - Specification:

- Water/ Powder: 24-26ml/100gm
- Mixing Time: 45 seconds wet
- Working Time: 5 minutes dry
- Setting Time: 8-12 minutes
- Hard Set (Initial): 30 Minutes
- Wet Compressive Strength: 400 kg/cm²
- Dry Compressive Strength: 800 kg/cm²
- Linear Expansion (Max): 0.08%

Shelf Life and Storage:

- Best before 24 months under proper storage.
- Store at a temperature between 10°C to 30°C.